



国家陶瓷检测重点实验室联盟
STATE KEY TESTING LABORATORY UNION OF CERAMICS
国家建筑卫生陶瓷检测重点实验室
STATE KEY TESTING LABORATORY OF BUILDING CERAMICS AND SANITARY WARE
佛山海关综合技术中心
COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN CUSTOMS



中国认可
国际互认
检测
CNAS L1978 190000122473



TEST REPORT

Test report No.: **25202300603**

Page 1 of 1

Applicant: BESTVIEW(FUZHOU) IMPORT & EXPORT CO.,LTD

Address of Applicant: 24F FORTUNE BUILDING 168 HUDONG ROAD FUZHOU CHINA 350003

Name of Sample: PORCELAIN MOSAIC

Mark of Samples: — Sizes of Sample: —

Source of Samples: Samples selected by applicant Quantity of Samples: 5 Pieces

Received on: 2023-03-01 Test Date: 2023-03-02~2023-03-03

Test Standard: 1.ASTM C 1027-19 *Standard Test Method for Determining Visible Abrasion Resistance of Glazed Ceramic Tile*
2.ASTM C 1895-20 *Standard Test Method for Determination of Mohs Scratch Hardness of Ceramic Tile*
3.ANSI A326.3-2017 *American National Standard Test Method for Measuring Dynamic Coefficient of Friction of Hard Surface Flooring Materials*

Results of Inspection:

Test Item	Test Method	Test Result
Visible Abrasion Resistance	ASTM C1027-19	Class III
Mohs Scratch Hardness	ASTM C 1895-20	Highest Numerical Hardness Point Which Did Not Produce Scratch: 6 Lowest Numerical Hardness Point Producing Scratch: 7
Dynamic coefficient of friction	ANSI A326.3-2017	Wet DCOF Value (μ D): 0.64


*** **

End of Test Report

Stamp of inspection unit



Authorized Signatory 肖景洪 Date 2023-03-04
XIAO JINGHONG



声明: 1. 我们已尽所知所能实施上述检验, 不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务; 2. 未经本实验室书面许可, 不得部分复制本报告; 3. 本报告仅是样品的检测结果;
4. 本报告所述的样品信息为委托单位自行声明, 实验室不负责其真实性。
Notes: 1. All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations.
2. This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 3. The results in this report apply to the samples only. 4. The product information are declared by applicant, and laboratory is not responsible for the authenticity.
广东省佛山市禅城区魁奇一路澜石(国际)金属交易中心十八座二楼 2/F, Building 18, Lanshi International Metal Exchange Center, Kuaiqi Road, Chancheng District, Foshan, Guangdong, China 528000
Tel: 86-757-83960558 83827991 Fax: 86-757-83827971 E-mail: fsiqtc@163.com

FSIQTC-T 2(1)/A